
Testing to perfection.

We have always offered the most trusted, field-proven products in the industry. Coupling this with our new manufacturing capabilities and investment in testing technology allows us to offer our customers the widest product range on the market.







	Compression Deflection / PSI (lbs per square inch)							Durometer*	Resiliometer
PRODUCT NAME	10%	20%	30%	40%	50%	60%	70%	SHORE 00	REBOUND
G-257	6.6	9.9	15.5	19.9	26.4	40.8	56.4	62	56
DS-3000	11.3	16.8	18.6	21.0	26.5	37.6	81.3	68	42
T-75	19.2	28.4	40.4	51.5	70.9			75	49
DS-75	16.4	32.6	41.0	52.1	81.0			75	44
61-X	15.6	30.9	41.4	48.7	60.0			76	43
6110	16.9	29.9	38.2	47.1	93.5			76	48.65
RD-73	13.3	20.3	23.4	28.0	31.5			70	39.5
BlueZoom	11.8	16.3	21.4	24.7	28.5			69	38.5
6118	9.7	16.6	25.0	35.4	49.4			68	36
F-70	13.0	17.6	23.8	30.5	45.7			70	41
B-65	8.4	19.7	25.5	29.1	30.5			65	42.5
6220	9.0	18.4	25.8	32.2	33.9			65	34
K-60	8.3	12.3	16.2	20.5	27.0			60	40.5
6320	8.9	15.4	21.8	31.6	50.7			60	39
Dura-Bull	24.7	43.3	55.7	66.7	94.2	157.3		83	54
GN-88	39.3	66.6	76.8	92.1	114.3			88	33
CORK	58.2	97.6	108.0	143.6	224.6			90	32.5
Econo-Cork	56.0	107.6	129.8	172.2	232.7			90	30.5

^{*}Manufacturers range of Durometer is + - 5



Toll free: 1-800-331-6480 Or call: 636-671-9600 Fax: 636-671-9605 12955 Maurer Industrial Drive St. Louis, MO 63127 www.diansuply.com